

AMENDMENT TO THE CLAIMS:

Please amend claims 1-6, and add new claims 7-10, as shown below.


This listing of claims will replace all prior versions and listings of claims in the Application:

Claim 1 (currently amended): A ~~power storage device~~secondary electrochemical cell comprising a cathode and an anode,

wherein:

the cathode comprises a cathode layer comprising nitroxyl polymer, and a cathode collector;

[[a]]the nitroxyl polymer [[which]] has a nitroxyl cation partial structure represented by the following chemical formula (I) in oxidation state and has a nitroxyl radical partial structure represented by the following chemical formula (II) in reduction state, ~~in a cathode;~~ employing a reaction for transferring an electron between the two states represented by the following equation (B) as an electrode reaction of the cathode:



~~and using a~~the anode comprises a lithium or lithium alloy [[anode]] as an anode active material;

~~wherein~~ the cathode ~~layer~~contains is impregnated with an electrolyte having an electrolyte salt dissolved in a solvent; and


the nitroxyl polymer is applied onto the cathode collector and is in direct contact with the anode.

Claim 2 (currently amended): The ~~power storage device~~secondary electrochemical cell according to claim 1, wherein a lithium-tin alloy or a lithium-silicon alloy is used as the anode active material.

Claim 3 (currently amended): The ~~power storage device~~secondary electrochemical cell according to claim 1, ~~using a~~wherein the cathode collector ~~having~~comprising an aluminum plate and a conductive auxiliary layer comprising carbon as a main component, and the conductive auxiliary layer formed and integrated ~~[[on]]the an aluminum electrode as a cathode collector~~plate.

Claim 4 (currently amended): The ~~power storage device~~secondary electrochemical cell according to claim 1, ~~[[using]]~~wherein the cathode collector comprises a carbon paper ~~as a cathode collector~~.




Claim 5 (currently amended): The ~~power storage device~~secondary electrochemical cell according to claim 1, wherein the nitroxyl polymer is a polymer compound having a cyclic nitroxyl structure represented by the following chemical formula (5) in oxidation state:



wherein each of R₁ to R₄ independently represents an alkyl group, and X represents a divalent group so that the chemical formula (5) forms a 5- to 7-membered ring, while X constitutes a part of a side chain or a main chain of the polymer.

Claim 6 (currently amended): The ~~power storage device~~secondary electrochemical cell according to claim 5, wherein the nitroxyl polymer is a polymer compound having a side chain

containing a residue which removes at least one hydrogen atom bonded to an element forming at least one cyclic nitroxyl structure selected from the group consisting of a 2,2,6,6-tetramethylpiperidinoxyl cation represented by chemical formula (6), a 2,2,5,5-tetramethylpyrrolidinoxyl cation represented by chemical formula (7) and a 2,2,5,5-tetramethylpyrrolinoxyl cation represented by chemical formula (8).



Claim 7 (new): The secondary electrochemical cell according to claim 1, wherein a content of electro-conductivity imparting material in the cathode layer is 50% by weight or less.

Claim 8 (new): The second electrochemical cell according to claim 1, wherein the cathode layer consists essentially of the nitroxyl polymer.

Claim 9 (new): The second electrochemical cell according to claim 1, wherein the cathode layer consists of the nitroxyl polymer and a polymer electrolyte.

Claim 10 (new): The second electrochemical cell according to claim 1, wherein the secondary electrochemical cell is a coin-type cell.